



RECEIVED

MAR 19 2003

TC 1700

PATENT APPLICATION

#174/B  
3/26/03  
iC

Docket No. KPC-289  
Serial No. 09/804,293

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Attorney Docket No. KPC-289

In re design Application of  
NAKAO et al.

Confirmation No.: 9278

Serial No. 09/804,293

Group Art Unit: 1712

Filed: March 13, 2001

Examiner: SELLERS, ROBERT E

Title: COLD SETTING COATING COMPOSITION (AS AMENDED)

**RESPONSE TO RESTRICTION REQUIREMENT AND OBJECTION**

**AND PRELIMINARY AMENDMENT**

Commissioner for Patents  
Washington, D.C. 20231

Sir:

**Restriction/Election Requirement**

In response to the Office Action dated January 15, 2003, Applicants hereby elect Group I, including claims 10-15, drawn to a composition comprising a urethane-modified vinyl resin, and a species of urethane modified vinyl resin (A) such as the glycidyl methacrylate/styrene/n-butyl methacrylate/i-butyl methacrylate/2-ethylhexylmethacrylate as epoxy group-containing vinyl copolymer (a), linseed oil fatty acids as fatty acid (b) and hexamethylene diisocyanate as isocyanate group-possessing compound (c) shown in Production Example 1 without traverse.

**In the Specification:**

Beginning at page 30, line 1, please rewrite the following Table 2 as set forth below in clean form. Additionally, in accordance with 37 CFR 1.121(b)(1)(iii), the


amended portion of Table 2 is set forth in a marked-up version in the pages attached to this Amendment as Appendix I.

Table 2

		Example								Comparative Example	
		5	6	7	8	9	10	11	12	2	3
Urethane-modified vinyl resin	Kind	A-5	A-5	A-5	A-6	A-5	A-5	A-7	A-8	A-9	
	Amount	50	50	50	50	50	70	50	50	50	
Polymer dispersion	Kind	B-1	B-2	B-3	B-1	B-1	B-1	B-1	B-1	B-1	B-3
	Amount	50	50	50	50	50	30	50	50	50	100
Cobalt naphthenate		0.3	0.3	0.3	0.3		0.3	0.3	0.3	0.3	0.3
Lead naphthenate		1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0
Manganese naphthenate						0.3					
Mineral spirit		20	20	20	20	20	20	20	20	20	20
JR603		40	40	40	40	40	40	40	40	40	40
Disparlon 6900-10		2	2	2	2	2	2	2	2	2	2
BYK-066		0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8

Page 24, after line 18, please insert the following paragraph:

FANCRYL FA-512MT is shown in the following formula:



### REMARKS

Election of the species has been made according to suggestion by the Examiner. Substitute specification has been amended by the foregoing amendment to overcome the objections to the substitute specification. No new matter has been entered.